

PRODUCT DATA

FASSICLOR

DESCRIPTION

Solvent borne chlorinated rubber paint.

MAIN PROPERTIES

Alkali and acid resistant - excellent water resistance - U.V. stable.

RECOMMENDED USES

Decorative painting of swimming pools or ponds in concrete.

TECHNICAL DATA

Appearance:	Satin gloss (gloss 60°): ± 47%
Colour:	White, azure blue, water green, pearl grey
Density:	1.2 - 1.3 g/cm ³
Solids Content:	In volume: 28 - 33%
	In weight: 49 - 56%
Recommended film thickness:	Wet film: ± 165 micron (cons.: 6 m ² /l)
	Dry film: ± 50 micron (cons.: 6 m ² /l)
VOC-content:	Max. 640 g/l
Flashpoint:	> 39°C

Drying times 20°C/50% r.h.

To touch: 1½ hours

To handle: 3 hours

To recoat: 24 hours

Full hardness 12 days

Coverage

Theoretical: 2 coats of ± 6 m²/l per coat

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Apply without priming coat on an old chlorinated rubber paint (after cleaning) or on a hardened and dry concrete substrate (maximum humidity degree 5%). Attention: since Fassiclor is no waterproofing product, the concrete substrate must be waterproof!

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush: If necessary, dilute slightly with Thinner 22.

Roller: Apply the first coat with brush by preference, if necessary dilute slightly with Thinner 22.

Air-atomised spray: If necessary, dilute slightly with Thinner 22.

Airless spray: Dilute with ± 10 – 20% Thinner 22.
Nozzle: 018 / Pressure: 200 bars.

Cleanup: Thinner 22

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com

PRODUCT DATA

FASSICLOR

APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.

REMARKS

When using in indoor swimming pools, especially during airless spraying, it is advisable to wear a mask due to limited ventilation.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com